Artificial fusion protein to facilitate calcium carbonate mineralization on insoluble polysaccharide for efficient biocementation

Thiloththama H. K. Nawarathna[†], Kazunori Nakashima^{‡*}, Tetsuya Kawabe[†], Wilson Mwandira[†], Kiyofumi Kurumisawa[‡], Satoru Kawasaki[‡]

[†] Division of Sustainable Resources Engineering, Graduate School of Engineering, Hokkaido University, Kita 13, Nishi 8, Kita-Ku, Sapporo 060-8628, Japan

[‡] Division of Sustainable Resources Engineering, Faculty of Engineering, Hokkaido University, Kita 13, Nishi 8, Kita-Ku, Sapporo 060-8628, Japan

*Corresponding author (K. Nakashima)

TEL/FAX: +81-11-706-6322

E-mail: <u>k.naka@eng.hokudai.ac.jp</u>

ABSTRACT

Biomineralization is a process of mineral formation in living organisms. Compared with nonbiogenic minerals, biominerals can be defined as organic-inorganic hybrid materials that have excellent physical and optical properties. In the current study, an artificial protein mimicking the outer shell of crayfish, composed of CaCO₃, chitin, and proteins, was developed to facilitate organic-inorganic hybrid material formation by precipitation of calcium carbonate on the chitin matrix. The fusion protein (CaBP-ChBD) was constructed by introducing a short-sequence calcite-binding peptide (CaBP) into the chitin-binding domain (ChBD). Calcium carbonate precipitation experiments by enzymatic urea hydrolysis revealed that a significant increase of the CaCO₃ formation was achieved by adding CaBP-ChBD. Also, CaCO₃ was efficiently deposited on chitin particles decorated with CaBP-ChBD. Most interestingly, CaBP-ChBD would improve the performance in sand solidification more efficiently and sustainably in the process of biocementation technique. Developed recombinant protein could be used for the sustainable production of organic-inorganic green materials for engineering applications.

Keywords: Recombinant protein, Hybrid materials, Biopolymer, Calcium Carbonate, Biocementation

INTRODUCTION

Biomineralization is a process of crystal nucleation and growth, and it is mostly controlled by organic macromolecules such as proteins, polypeptides, and polysaccharides.^{1,2} Therefore, biominerals can be simply defined as organic-inorganic hybrid materials, and they are essential components in living organisms to support their different functions.^{3,4} Compared with nonbiogenic minerals, biominerals are formed under mild conditions at near-neutral pH and ambient temperature, and they exhibit higher mechanical strength than nonbiogenic minerals.³ Hydroxyapatite in the bones and teeth of mammals,⁵ calcium carbonate in molluscan shells,⁶ and amorphous silica in diatoms⁷ and marine sponges⁸ are well-known examples of biomineral

Among the biominerals available in nature, most of them are calcium-bearing minerals, and calcium carbonate (CaCO₃) is the most dominant type of biomineral.⁹ Coccoliths of coccolithophores, exoskeletons of crustaceans, and the nacre of mollusk shells mainly consist of biogenic CaCO₃ and exhibit excellent mechanical and optical properties.^{9,10} For example, the strength of the nacre of a mollusk shell is 3000 times higher than that of pure CaCO₃.¹¹ Nacre has a brick and mortar structure, in which inorganic plate-like aragonite CaCO₃ crystals (brick) are cemented with pre-organized chitin sheets (mortar).¹² This structure provides the extensive mechanical strength of the nacre.

During the formation of biogenic CaCO₃, matrix proteins act as a template or starting point, and they play a vital role in the efficient formation of minerals on the organic matrix. To date, a number of proteins have been identified from the various species associated with the formation of CaCO₃ biominerals.^{13–15} One of the best examples available in nature is the exoskeleton of the crayfish, in which CaCO₃ is deposited upon a chitin matrix with the assistance of the acidic protein CAP-1.^{4,16} CAP-1 has a "Rebers–Riddiford" consensus sequence, and it helps the binding to the chitin. Also, this protein tends to be acidic owing to the associated seven acidic amino acids at the C-terminus, which facilitates CaCO₃ formation.^{16,17} Similarly, chitin-binding type 2 domain (ChtBD2) has been identified from the multifunctional matrix protein, hichin from the mantle of *H. cumingii*, which is involved in shell and pearl biomenralization.¹⁸ The matrix protein, PPP-10 in the periostracum of the pearl oyster has a chitin binding ability and mainly support the self-assembly of the periostracum.¹⁹ Similarly, blue mussel shell protein 120 (BMSP-120) in the nacreous of the *Mytilus galloprovincialis* has peritrophin-A chitin binding domain, which facilitates the nacreous layer formation,²⁰ and interlamellar matrix protein pearlin in nacreous layer of *Pinctada margaritifera* contributes to calcium and chitin binding in nacreous layer.²¹

In addition to the strength gain, biomacromolecules control the formation of minerals with nano-structural regularity and specific crystallographic phases, morphologies, and orientations,¹⁵ which improve the fracture resistance and toughness of biogenic minerals, making them more feasible to use for certain industrial applications.²²

By considering all these factors, researchers have recently attempted to mimic the concept of biomineral formation in the synthesis of CaCO₃-organic hybrid materials for their associated excellent physical and optical properties. CaCO₃ biominerals can be extensively used in biomedical applications. Alternatively, the biological formation of CaCO₃ by enzyme-induced carbonate precipitation (EICP) has recently gained much attention as an efficient cementing material to solidify weak soils.^{23–25}

EICP is a biogeochemical process catalyzed urease.²⁶ Urease hydrolyze urea to produce ammonia and bicarbonate ions. Bicarbonate ions instantaneously give CaCO₃ in the presence of Ca²⁺ ions under alkaline condition, which is induced by the generated ammonia. Formed CaCO₃ can act as a cementing material to bind sand particles, and this process or technique is called biocementation. In biocementation by EICP, effective filling of the pore spaces between sand particles with CaCO₃ is essential to get a better strength and stiffness. CaCO₃ formation by the EICP process can be further increased by adding biomacromolecules such as xanthan gum, guar gum, poly (acrylic acid) (PAA) etc.^{27,28} In this process, the efficient deposition of CaCO₃ on organic materials is essential to obtain desired strength.

To fulfill these expectations, the aim of this research was to develop a novel artificial fusion protein that could be directed toward efficient precipitation of CaCO₃ on chitin. Chitin was selected as an organic matrix because it is one of the most abundant, insoluble, linear polysaccharides available in nature, and it is mostly associated with CaCO₃ biomineralization.^{12,16,29} The chitin-binding domain (ChBD) from chitinase was used as the chitin-binding site because it has a high binding affinity to chitin,³⁰⁻³² whereas a short sequence of calcite-binding peptide (CaBP) was used as the calcite-binding site.^{33,34} The fusion protein had both a calcium-binding site and a chitin-binding site, which facilitated the efficient precipitation of CaCO₃ on the chitin matrix (Fig. 1). The effect of the novel fusion protein on CaCO₃ crystallization and sand densification were investigated using urease-based mineralization. This study is the first to address the use of urease-based mineralization to generate organic composite materials using a newly developed recombinant protein.

MATERIALS AND METHODS

Materials

The synthetic gene of the chitin-binding domain (ChBD) from chitinase A1 from *Bacillus circulans* WL-12 (GenBank: AAA81528.1) was purchased from Eurofins Genomics (Tokyo, Japan) and optimized for expression in *E. coli*. Calcite-binding peptide (CaBP: DVFSSFNLKHMR) derived from the phage-display system^{33,34} was purchased from Gen Script (Tokyo, Japan). Tryptone and yeast extract were purchased from BD Biosciences Advanced Bioprocessing (Miami, FL, USA). Ampicillin and isopropyl β -D-

1thiogalactopyranoside (IPTG) were obtained from Nacalai Tesque (Tokyo, Japan). Chitin powder was purchased from Wako Pure Chemical Industries Ltd. (Tokyo, Japan). All other organic materials and chemical reagents were purchased from Wako Pure Chemical Industries Ltd.

Gene construction and protein expression

The amino acid sequence of the fusion protein (CaBP-ChBD) in this work is shown in Fig. 1(A). The gene encoding the fusion protein was constructed using a forward primer (AAGGAGATATACATATGGATGTGTTTAGCTCGTTCAACCTGAAACATATGCGCA AGCTTGCCTGGCAAGTCAACACTGCG) containing the CaBP gene to introduce CaBP at the N-terminal region of ChBD. The target gene for CaBP-ChBD was amplified by a polymerase chain reaction (PCR) using Prime Star Max DNA polymerase (Takara Bio, Japan) using a primer set of the forward primer described above and a reverse primer (GGTGGTGGTGGTGCTCGAGCTGCAGCTGCCACAACGCTG). The amplified CaBP-ChBD gene was inserted into the pET-22b(+) vector, which was linearized using *Xho* I and *Nde* I restriction enzymes (New England Bio Labs, Japan) using the In-Fusion system (Takara Bio) to obtain the expression vector pET-CaBP-ChBD. Here, restriction enzyme sites were selected to incorporate a His-tag at the C-terminus of CaBP-ChBD. *E. coli* DH5 α was transformed with pET-CaBP-ChBD and grown in LB-Amp medium (5 mL) for 16 h at 37 °C and 160 rpm. The plasmid was extracted and subjected to DNA sequencing (Eurofins Genomics).

E. coli BL21 (DE3) transformed with pET-CaBP-ChBD was cultured at 37 °C and 160 rpm until the OD₆₀₀ reached 0.5. Then, protein expression was induced by adding 0.5 mM IPTG and shaking at 30 °C and 160 rpm for 24 h. Cells were harvested by centrifugation of the cell suspension (8000 × g, 4 °C, 10 min) and resuspended in lysis buffer. Cells were disrupted by ultrasonication (VCX-130, Sonics & Materials Inc., USA; strength: 30%, 2 min), and the cell

lysate was centrifuged (4 °C, 12,000 × g, 20 min) to remove cell debris. The supernatant was subjected to His-tag purification using Bio-Scale Mini Nuvia IMAC Cartridges (Bio-rad Laboratories, Inc., Tokyo, Japan) because the protein was expressed as a soluble protein, which was confirmed by SDS-PAGE (Atto Company Limited, Tokyo, Japan). The purified protein was concentrated using Amicon Ultra-4 (3 kDa), and then the buffer was replaced with Tris-HCl (pH 9). Unmodified ChBD was prepared similarly to CaBP-ChBD except for using a forward primer (AAGGAGATATACATATGGCCTGGCAAGTCAACACT) that does not contain the CaBP gene.

Solid-binding assay

The chitin-binding ability of CaBP-ChBD was studied. Chitin powder (10 mg) was mixed with CaBP-ChBD (1ml, 0.04 mM) in 50 mM Tris-HCl buffer (pH 9) and shaken at 25 °C. Samples were collected at different time intervals (0, 5, 10, 15, 30, 60, 120, 180 min), followed by centrifugation (13,000×g, 10 min). The protein concentration of the supernatant was measured using the Bradford method to calculate the adsorption of CaBP-ChBD on chitin. Moreover, the supernatant was analyzed by SDS-PAGE to detect the protein.

The binding ability of CaBP-ChBD (1ml, 0.04 mM) to CaCO₃ in 50 mM Tris-HCl buffer (pH 9) was analyzed using a commercial CaCO₃ powder (purity 99.5%; Wako Pure Chemical Industries Ltd., Tokyo, Japan) in a similar manner to the procedure described above.

Effect of additives on urease-catalyzed CaCO₃ precipitation

CaCO₃ precipitation experiments were conducted by hydrolysis of urea by extracted jack bean urease (2.5 U/mL, Wako Pure Chemical Industries Ltd., Tokyo, Japan) in the presence of 0.75 mol/L of CaCl₂ and 0.75 mol/L of urea. Urease can hydrolyze urea to produce ammonia and bicarbonate ions. Bicarbonate ions instantaneously give CaCO₃ in the presence of calcium ions under alkaline conditions, which are induced by the generated ammonia.^{27,28} Experiments were conducted without any peptides/proteins, with ChBD (75 μ g/mL), with CaBP (75 μ g/mL), with the combination of ChBD (75 μ g/mL) and CaBP (75 μ g/mL), with fusion protein CaBP-ChBD (75 μ g/mL). All experiments were conducted with or without chitin (2.5 mg/mL).

The reaction mixture was shaken at 25 °C and 160 rpm for 24 h, followed by centrifugation (24 °C, 14,200×g, 10 min) to separate the precipitate and supernatant. The dry weights of the precipitates were measured after oven drying at 90 °C for 24 h. The effect of bovine serum albumin (BSA; 75 μ g/mL) on the CaCO₃ precipitation with or without chitin (2.5 mg/mL) was also investigated.

Deposition of CaCO₃ on chitin

Calcium carbonate deposition on chitin mediated by CaBP-ChBD was conducted. First, CaBP-ChBD (75 µg/mL) was mixed with chitin (2.5 mg/mL) at pH 9 for 24 h to achieve adsorption equilibrium. Subsequently, EICP reaction was conducted similarly as described in the previous section. The same CaCO₃ formation reactions were also performed without any additives, with only CaBP-ChBD (75 µg/mL), with only chitin (2.5 mg/mL). After CaCO₃ formation, the precipitates were washed twice with 15 mL of distilled water, followed by lyophilization for 24 h for analysis. After coating the materials using a carbon coater (EC-32010C, JEOL, Japan), the morphology of the materials was analyzed using scanning electron microscopy (SEM; JSM-IT200 InTouchScope, JEOL, Japan) equipped with energy-dispersive X-ray spectroscopy (EDS). X-ray diffraction pattern was recorded using MultiFlex (Rigaku Co., Ltd., Tokyo, Japan; analysis condition: 40 kV, 40 mA, 2.0°/min) to identify the polymorphs of the precipitated CaCO₃.

Sand solidification by EICP and MICP

Enzyme-catalyzed CaCO₃ formation on silica sand was conducted without additives (control), with CaBP-ChBD, with chitin, and with both chitin and CaBP-ChBD. Oven-dried (110 °C for 2 days) Mikawa silica sand (14.5 g, mean diameter $D_{50} = 0.6$ mm, 97.65 % SiO₂) was placed in a 10 mL syringe with three layers and each layer was tamped down by a hammer for 20 times. Cementation solution (0.75 M urea, 0.75 M CaCl₂, 10 mL) supplemented with urease (2.5 U/ml) was injected into the syringe, and then drained out from the outlet to keep the solution at 2 mm above the surface of the sand. To examine the effect of additives on solidification, CaBP-ChBD (75 µg/mL), chitin (0.145 g), or both of CaBP-ChBD (75 µg/mL) and chitin (0.145 g) was introduced in sand solidification. In the case of addition of both CaBP-ChBD and chitin, CaBP-ChBD was first mixed with chitin at pH 9 for 24 h to achieve adsorption equilibrium before mixing with sand. Experiments were done in an incubator at 25 °C for 7 days. After 7 days, samples were removed from the syringe by cutting and samples were analyzed by SEM to understand the behavior of the CaBP-ChBD and chitin on the solidification of silica sand.

Furthermore, sand solidification was done by microbial-induced carbonate precipitation (MICP), where urease producing bacteria *Pararhodobacter* sp. SO1^{35,36} was used. Bacterial culture was prepared as previously described.³⁷ Oven dried Mikawa silica sand (43.5 g) was placed in a 30 mL syringe in three layers (14.5 g each) and twenty hammer blows were given to each layer. Bacteria suspension (16 ml, $OD_{600} = 1$) was injected into the syringe and kept it 20 min for the better fixation of the bacteria into the sand particles, followed by draining out of the solution from the outlet, leaving the solution at 2 mm above the surface of the sand. Then, cementation solution (20 mL; 0.3 M urea, 0.3 M CaCl₂, 3 g/L nutrient broth (BD Biosciences Advanced Bioprocessing, Miami, FL, USA)) was added to the syringe. Then, the solution was drained out from the outlet keeping 2 mL of the solution above the surface to

maintain the sand in immersed condition. Experiments were conducted in an incubator at 30 °C for 14 days. Bacteria solution (16 mL) was injected again at seventh day. Similar experiments were conducted by adding CaBP-ChBD (75 μ g/mL), chitin (0.435 g), and both of chitin and CaBP-ChBD. In the case of addition both of CaBP-ChBD and chitin, CaBP-ChBD was adsorbed on chitin to reach adsorption equilibrium before mixing with sand. After 14 days, samples were removed from the syringe by cutting. Uniaxial compressive strength (UCS) and the fracture strain of the cemented samples were obtained by using uniaxial compressive machine (INSTRON 5500R; an Instron loading frame, screw-type, capacity: 250 kN) with loading speed of 0.036 mm/min.

RESULTS AND DISCUSSION

Gene construction and protein expression

Expression vectors containing the target genes (CaBP-ChBD, ChBD) were successfully constructed and confirmed by DNA sequencing. The target proteins were expressed successfully as soluble proteins in *E. coli* according to the SDS-PAGE analysis, as shown in Fig. S1. Generally, lower temperatures were more favorable for IPTG to induce protein expression and to prevent the misfolding of proteins and the formation of inclusion bodies. However, CaBP-ChBD and ChBD were not expressed at lower temperatures around 15 °C; they were successfully expressed at ambient temperature (30 °C). Favorable expression temperature depends on the type of protein, and most chitin-binding proteins are expressed at ambient temperature.^{32,38} The expressed proteins were successfully purified using an IMAC Ni-charged column and eluted with a high concentration of imidazole, as shown in Fig. S2. The purified proteins were concentrated by ultrafiltration, and the buffer was completely replaced with Tris-HCl buffer (pH 9) because ChBD from chitinase A1 has a higher binding affinity to chitin at higher pH.³⁰

Solid-binding assay

The binding ability of CaBP-ChBD to chitin was evaluated by incubating the protein with insoluble chitin. As shown in Fig. 2(A), 80% of the CaBP-ChBD was adsorbed on insoluble chitin within 3 h. The SDS-PAGE shown in Fig. 2(B) confirmed the ability of CaBP-ChBD to adsorb on insoluble chitin. The obtained results are consistent with previous observations for the binding assay of ChBD from chitinase A1 on colloidal chitin³⁰. Because the isoelectric point (pI) of the CaBP-ChBD was around 8.9, the net charge of the protein at pH 9 was almost zero. Chitin shows hydrophobic nature because of the acetyl group³⁹ and glucopyranose ring in *N*-acetylglucosamine unit of chitin. Hence, hydrophobic interaction between the protein and chitin polymer chain would be a dominant factor in adsorption.

Similarly, the binding ability of CaBP-ChBD on CaCO₃ was evaluated by incubating the protein with CaCO₃ powder. The CaBP-ChBD was not efficiently adsorbed on CaCO₃, and only 30% of the protein was adsorbed after 24 h compared with the initial (0 h) protein concentration. Although CaBP itself has a high affinity for CaCO₃,^{33,34} the binding ability would significantly decline when CaBP (1.5 kDa) is fused with ChBD (5 kDa), probably because of steric hindrance by the protein.

Effect of additives on urease-catalyzed CaCO₃ precipitation

Urease can hydrolyze urea and produce $CaCO_3$ in the presence of calcium ions (Ca^{2+}) .^{27,28} CaCO₃ precipitation was conducted by urease under various experimental conditions. The amount of CaCO₃ precipitates in the presence of proteins with or without chitin are shown in Fig. 3. With no additive (no protein, without chitin), the amount of precipitate was about 0.05 g, which can be estimated to 16% conversion considering that the maximum amount of CaCO₃ is 0.3 g in complete reaction (100% conversion). In the presence of proteins, the amount of

precipitate increased drastically. The increase was more significant in the presence of ChBD moiety, where the conversion was 49% for ChBD, 56% for ChBD + CaBP, and reached to 66% for CaBP-ChBD. On the other hand, a small increment of the precipitate was obtained by adding chitin compared to that without chitin.

CaCO₃ formation in the presence of proteins is mostly related to the amino acid sequence of the protein. Amino acids can act as nucleation and growth-promoting molecules by reducing the activation energy of nucleation and promoting the growth of the crystals.⁴⁰ Generally, most of the proteins that facilitate CaCO₃ biomineralization are rich in acidic amino acids.^{9,16} In contrast, few studies have revealed that acidic amino acids inhibit CaCO₃ crystallization and promote the stabilization of the unstable phase of CaCO₃.^{28,41} Also, some matrix proteins that facilitate CaCO₃ biomineralization are rich in basic amino acid residues.⁴² In our previous studies, we found that positively charged polypeptides and polysaccharides also have the ability to increase CaCO₃ formation.^{37,43}

The CaBP used in this study was not rich in acidic amino acids, and only one aspartic acid residue was present.³³ However, it was rich in basic amino acids and contained lysine, histidine, and arginine residues. The pH of the reaction mixture was 9, and at this pH, arginine was completely positively charged, lysine was partially charged, and histidine was almost electroneutral because the dissociation constants (pK_a) of histidine, lysine and arginine are 7, 9, and 11, respectively.⁴⁴ However, at pH 9, the carboxylic group of the aspartic acid is mostly negatively charged. Hence, CaBP can be classified as a basic peptide with a positive charge.³⁴

The amino acid sequence of the ChBD was rich in basic amino acids and poor with acidic amino acids. It contained two lysines, one histidine, and one glutamic residue. The presence of the higher amounts of basic amino acid residues in both CaBP and ChBD would be the most reasonable reason for the good performance of the CaBP-ChBD in terms of CaCO₃ formation.

Not only the charged amino acids but also some of the amino acids with uncharged polar side chains had a considerable influence on the CaCO₃ crystallization. CaBP-ChBD contained cysteine, serine, and asparagine residues, which had a considerable influence on the CaCO₃ crystallization. In nature, cysteine-rich mineral-associated proteins can be found in lustrin A,⁴⁵ in the nacre of abalone and perlwapin.⁴⁶

As shown in Fig. 3, CaBP alone did not contribute significantly to CaCO₃ formation. Therefore, associated ChBD would have a considerable influence on the formation of CaCO₃. Instead of the CaBP-ChBD, ChBD itself could increase the CaCO₃ formation. It is difficult to give an exact reason for this behavior of the ChBD. However, chitin and chitin-binding proteins are mainly associated with CaCO₃ biomineralization. In the exoskeleton of the crustacean⁴⁷ and the nacre of mollusk shells,¹² CaCO₃ is deposited on the chitin matrix, and this chitin matrix contributes significantly to the morphology and polymorphism of the crystals. Also, in the exoskeleton of crayfish, CaCO₃ is deposited upon the chitin matrix with the help of an acidic peptide containing a chitin-binding domain.¹⁶ Therefore, ChBD would have a significant influence on CaCO₃ formation and morphology change, as well as its ability to bind to chitin.¹⁸

Another interesting point is that adding CaBP and ChBD separately did not result in better performance as did CaBP-ChBD. Most probably, the structure of CaBP-ChBD and its molecular arrangement had a significant influence on the CaCO₃ formation. Structural changes in the protein under alkaline conditions can also contribute significantly to its superior ability to form CaCO₃. Also, the close proximity of CaBP and ChBD may have had a considerable influence on the CaCO₃ formation. Further studies should be conducted to check the secondary structure of the protein to give a much better conclusion.

Deposition of CaCO₃ on chitin

The morphology and the deposition of CaCO₃ on chitin induced by urease were analyzed using SEM. Figure 4 shows SEM images of CaCO₃ formed in the presence of the additives. As shown in Fig. 4(a), the precipitates mostly consisted of the mixture of rhombohedral and spherical crystals with no additives. According to EDS analysis shown in Fig. 5(a) and XRD pattern given in Fig. 6(a), the precipitate is composed of vaterite and calcite crystals. Since vaterite has several morphologies and spherical shape is the most common type of morphology,⁴⁸ the spherical crystals in the precipitates could be vaterite. Supersaturation could possibly be a factor for the formation of vaterite crystals, meaning metastable state of CaCO₃ crystals are formed at higher supersaturation.⁴⁹

In contrast, cauliflower-shaped CaCO₃ was found in the presence of CaBP-ChBD as shown in Fig. 4(b). According to EDS analysis (Fig. 5b) and XRD pattern (Fig. 6b), the precipitates mostly consisted of calcite. The formation of the cauliflower-shaped crystals would be presumably induced by the assembling of pillar-shaped crystals, which are elongated type of rhombohedral crystal to *c*-axis direction when the crystallization takes place in the presence of low molecular weight additives such as CaBP-ChBD.⁵⁰ Previous research also reported that the formation of the cauliflower-shaped crystal is due to the adhering of pillar-shaped crystals,⁵¹ which is consistent with our observation. Also, slow crystallization process is favorable for the formation of pillar-shaped calcite crystals.⁵¹ In addition, protein aggregation is also possible in the presence of the CaCl₂, and adsorption of the protein aggregates to the growing crystals could make the crystals more porous and alter the morphology of the crystals.⁵² Furthermore, a high nucleation density, low size distribution, and the absence of rhombohedral crystals are characteristics of an efficient nucleator.⁵³ All of these characteristics can be seen in CaBP-ChBD. Therefore, CaBP-ChBD can be classified as an efficient nucleator for CaCO₃ crystallization. In the presence of chitin, rhombohedral crystals of CaCO₃ were deposited on the chitin particles as shown in Fig. 4(c) and Fig. 5(c). Previous studies also reported the formation of rhombohedral crystals upon a chitin matrix without matrix proteins.^{16,32} As confirmed in the XRD results (Fig. 6), the CaCO₃ crystals on chitin were identified as calcite. Previous work also reported that chitin has an ability to stabilize calcite crystal instead of vaterite.⁵⁴

Figure 4(d) shows CaCO₃ precipitation in the presence of both of CaBP-ChBD and chitin. Compared with the sample prepared only with chitin (Fig. 4c), chitin particles were covered not only with rhombohedral crystals but also with small flower-shaped particles. Based on EDS analysis in Fig. 5(d), these small particles on chitin were revealed to be CaCO₃. Since we could see both calcite and vaterite crystals in the precipitate according to XRD patterns in Fig. 6(d), the flower-shaped small particles would be vaterite while rhombohedral crystals should be calcite. Similar shape of vaterite crystal was also reported in the previous paper.⁵⁵ Density of the calcium ions on the surface of the polymer matrix is affecting greatly on the polymorphism of the CaCO₃ crystals. Higher calcium content on the surface of the polymer is more favorable for the stabilization of the least stable phase of the polymorphism, i.e. vaterite.⁵⁶ Accumulation of calcium ions on the chitin surface by the assistance of CaBP-ChBD might be a reason for the vaterite formation in the presence of both chitin and CaBP-ChBD. However, chitin surface was not uniformly covered with CaCO₃. Uniform distribution of CaCO₃ on the chitin could be achieved by changing the reaction rate of urea hydrolysis, which affects the deposition on chitin and the crystal size of CaCO₃. Changing reaction condition (with shaking or under stable) in EICP would be a factor in CaCO₃ deposition. In addition, adsorption rate of the protein into the CaCO₃ can be increased by reducing the crystal size. Size of the CaCO₃ crystals can be altered by changing the stirring time, speed and decreasing the rate of the solubilization of the salts.57,58

The behavior of CaBP-ChBD in terms of CaCO₃ formation and its morphology can be described in two ways. Fundamentally, protein can be adsorbed on chitin and chitin acts as a template for CaCO₃ to nucleate and grow. However, in the case of CaBP-ChBD, efficient precipitation of CaCO₃ on the chitin matrix occurred because of the associated CaBP, which helped to effectively form CaCO₃ on the chitin matrix. The protein itself contributed to the growth of CaCO₃ by being absorbed into the growing crystal faces.

CaCO₃ precipitation experiments were conducted using BSA as a control. BSA is a nonreactive protein that is abundant in plasma protein in mammals.⁵⁹ By adding BSA, small amounts (10%) of the precipitate were obtained. However, the increased amounts were not as significant as with CaBP-ChBD or other proteins. Also, the presence of uncovered chitin particles indicated that BSA did not contribute to the formation of CaCO₃ on the chitin matrix. Therefore, the results confirmed that the superior ability of CaBP-ChBD to form CaCO₃ is its unique property.

Sand solidification by EICP and MICP

Sand solidification by enzyme-catalyzed CaCO₃ formation, EICP, was conducted with additives (none, CaBP-ChBD, chitin, CaBP-ChBD and chitin). We could not obtain a solidification of silica sand with no additive under the present condition and treatment time while some agglomeration of sand was found in the presence of CaBP-ChBD, chitin, and combination of CaBP-ChBD and chitin (data not shown). Figure 7 shows the SEM images of sand samples after solidification test with and without additives. Without additive (control) as shown in Fig. 7(a), smaller size CaCO₃ particles have mainly been deposited on the sand surface. Obtained results are similar to the previous observations obtained for the solidification of sand using enzyme urease.^{60,61} In contrast to the control, rhombohedral CaCO₃ crystals and agglomeration of bigger sized crystals were formed on sand particles in the presence of CaBP-

ChBD (Fig. 7b). These crystal agglomerations would robustly form a better bridge between sand particles and led to densify the loose sand effectively. Furthermore, in addition to the crystal agglomerations, cylindrical shape crystals can be observed. The formation of cylindrical shape crystals would be due to the reassembly of the rhombohedral crystals and elongation into the *c*-axis when the crystallization takes place in the presence of low-molecular-weight additives.⁵³ Moreover, formation of the anisotropic shape of crystals greatly depends on the pH of the solution, where alkaline condition (pH>=9) is more favorable for the formation of anisotropic shape such as elliptical, star-like crystals etc.⁵⁷ In the presence of the chitin (Fig. 7c), a smaller number of polyhedron-shaped CaCO₃ crystals have been deposited on the chitin and sand surface. Interestingly, CaCO₃ formation was facilitated significantly and effectively with both CaBP-ChBD and chitin (Fig. 7d). The most important point is that pore spaces between the sand particle have been filled efficiently in this system. In the sand densification process, effective filling of the pore spaces between the sand particles are essential to get a better strength and stiffness for the sand specimen.⁶²

Furthermore, sand solidification by MICP using urease-producing bacteria was conducted with the additives. MICP is a promising approach for sand solidification compared to EICP because the microbes produce appreciable amounts of urease by culturing and sometimes keep producing during solidification. In addition, possible crystal nucleation sites on the surface of microbial cells would facilitate the formation of CaCO₃, which can act as a cementing material in solidification. In the present work, sand solidification was conducted using ureolytic bacterium *Pararhodobacter* sp. because it exhibits a high urease activity.⁶³ Experiments were conducted in an incubator at 30°C because bacteria have shown the highest urease activity at 30°C.⁶³ After 14 days of curing time (Fig. S3), UCS and fracture strain of the cemented sand samples were determined. The UCS value of 0.24 MPa was obtained without any additives

(control). The solidified sample with chitin gave lower strength (0.19 MPa) than the control. On the other hand, much higher strength could be achieved in the presence of CaBP-ChBD (0.44 MPa) and the combination of CaBP-ChBD and chitin (0.49 MPa). As mentioned above, efficient CaCO₃ formation leads to effective filling of the pore spaces between the sand particles, resulting in increased strength of the cemented samples. In the case of addition of only chitin, undesirable void space would be made between sand particles, resulting in the lack in bonding of the particles. Optimization of the amount of chitin could improve the strength.

In terms of fracture strain, the control sample gave the value of 0.014. The lower fracture strain was observed in chitin (0.003) and in CaBP-ChBD (0.007). In CaBP-ChBD system, higher USC value was obtained, but the material could become brittle because of the significant formation of solid CaCO₃ crystals. In contrast, higher fracture strain was obtained in the combination of CaBP-ChBD and chitin (0.017). The combination of CaBP-ChBD and chitin could make the solidified samples more ductile instead of brittle. The major drawback of the biocementation by MICP is brittleness of the solidified sample.⁶⁴ Therefore, the combination of CaBP-ChBD and chitin could give the best property of high strength and ductility. Further investigation is necessary for detailed evaluation of the effect of CaBP-ChBD and chitin, considering the shear behavior of solidified samples.

CONCLUSIONS

A novel recombinant protein CaBP-ChBD was developed by the fusion of ChBD with CaBP. CaBP-ChBD facilitated the formation of CaCO₃ on the chitin matrix. The morphology of CaCO₃ was significantly changed in the presence of CaBP-ChBD and chitin. In addition, the combination of CaBP-ChBD and chitin provided desirable properties in biocementation to improve the strength of loose sandy soil. The developed recombinant protein could be further modified or designed for optimization and functionalization for CaCO₃-organic hybrid materials, which can be used as an efficient and sustainable biocementation, as well as for other industrial applications in tissue engineering, biomedical engineering, etc.

AUTHOR INFORMATION

Corresponding Author

Kazunori Nakashima*

*Phone: +81-11-706-6322. Fax: +81-11-706-6322.

E-mail: <u>k.naka@eng.hokudai.ac.jp</u>

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work was partly supported by JSPS KAKENHI Grant Number JP18H03395 and JP21H03627. We would like to thank Prof. Y. Fujii at Hokkaido University for allowing us to use uniaxial compressive machine and R. Ishikawa at Technical Center of Engineering, Hokkaido University, for her support in SEM-EDS analyses.

SUPPORTING INFORMATION

SDS-PAGE analyses for the expression of CaBP-ChBD and ChBD, SDS-PAGE analyses for the His-tag purification of the proteins, Sand solidification by MICP with additives.

REFERENCES

- Mann, S. Biomineralization, Principles and Concepts in Bioinorganic Materials Chemistry; Oxford University Press: Oxford, U.K., 2001.
- (2) Estroff, L. A. Biomineralization. *Chem. Rev.* 2008, 108, 4329–4331, DOI 10.1021/cr8004789.
- (3) Arakaki, A.; Shimizu, K.; Oda, M.; Sakamoto, T.; Nishimura, T.; Kato, T. Biomineralization-inspired Synthesis of Functional Organic/Inorganic Hybrid Materials: Organic Molecular Control of Self-Organization of Hybrids. *Org. Biomol. Chem.* 2015, 13, 974-989, DOI 10.1039/C4OB01796J.
- (4) Kumagai, H.; Matsunaga, R.; Nishimura, T.; Yamamoto, Y.; Kajiyama, S.; Oaki, Y.; Akaiwa, K.; Inoue, H.; Nagasawa, H.; Tsumoto, K.; Kato, T. CaCO₃/Chitin Hybrids: Recombinant Acidic Peptides Based on a Peptide Extracted from the Exoskeleton of a Crayfish Controls the Structures of the Hybrids. *Faraday Discuss.* 2012, *159*, 483– 494, DOI 10.1039/C2FD20057K.
- (5) Dorozhkin, S. V.; Epple, M. Biological and Medical Significance of Calcium Phosphates. *Angew. Chem. Int. Ed.* 2002, *41*, 3130-3146, DOI 10.1002/1521-3773(20020902)41:17<3130::AID-ANIE3130>3.0.CO;2-1.
- (6) Stephen, W.; Lia, A. Design Strategies in Mineralized Biological Materials. J. Mater.
 Chem. 1997, 7, 689-702, DOI 10.1039/A604512J.
- (7) Chambers, A.; Park, C.; Baker, R. T. K.; Rodriguez, N. M.; Chen, P.; Lin, J.; Tan, K.L.; Brown, S.D.M.; Dresselhaus, G. Polycationic Peptides from Diatom Biosilica that Direct Silica Nanosphere Formation. *Science* 1999, 286, 1129-1132, DOI 10.1126/science.286.5442.1129.
- (8) Shimizu, K.; Cha, J.; Stucky, G. D.; Morse, D. E. Silicatein: Cathepsin L-like Protein in Sponge Biosilica. *Proc. Natl. Acad. Sci.* U. S. A. **1998**, *95*, 6234-6238, DOI

10.1073/pnas.95.11.6234.

- (9) De Oliveira, D. B.; Laursen, R. A. Control of Calcite Crystal Morphology by a Peptide Designed to Bind to a Specific Surface. J. Am. Chem. Soc. 1997, 119, 10627-10631, DOI 10.1021/ja972270w.
- (10) Gebauer, D.; Verch, A.; Borner, H. G.; Colfen, H. Influence of Selected Artificial Peptides on Calcium Carbonate Precipitation - A Quantitative Study. *Cryst. Growth Des.* 2009, *9*, 2398-2403, DOI 10.1021/cg801292p.
- (11) Jackson, A. P.; Vincent, J. F. V.; Turner, R. M.; Comparison of Nacre with Other Ceramic Composites. J. Mater. Sci. 1990, 25, 3173-3178, DOI 10.1007/BF00587670.
- (12) Sun, J.; Bhushan, B. Hierarchical Structure and Mechanical Properties of Nacre: A Review. *RSC Adv.* 2012, *2*, 7617-7632, DOI 10.1039/C2RA20218B.
- (13) Inoue, H.; Ozaki, N.; Nagasawa, H. Purification and Structural Determination of a Phosphorylated Peptide with Anti-calcification and Chitin Binding Activities in the Exoskeleton of Crayfish, Procambarus clarkii. *Biosci. Biotechnol. Biochem.* 2014, 65, 1840–1848, DOI 10.1271/bbb.65.1840.
- (14) Suzuki, M.; Saruwatari, K.; Kogure, T.; Yamamoto, Y.; Nishimura, T.; Kato, T.;
 Nagasawa, H. An Acidic Matrix Protein, Pif, is a Key Macromolecule for Nacre
 Formation. *Science* 2009, *325*, 1388-1390, DOI 10.1126/science.1173793.
- (15) Sudo, S.; Fujikawa, T.; Ohkubo, T.; Sakaguchi, K.; Tanaka, M.; Nakashima, K.
 Structures of Mollusc Shell Framework Proteins. *Nature* 1997, 387, 563-564, DOI 10.1038/42391.
- (16) Sugawara, A.; Nishimura, T.; Yamamoto, Y.; Inoue, H.; Nagasawa, H.; Kato, T. Self-organization of Oriented Calcium Carbonate/Polymer Composites: Effects of a Matrix Peptide Isolated from the Exoskeleton of a Crayfish. *Angew. Chem. Int. Ed.* 2006, *45*, 2876-2879, DOI 10.1002/anie.200503800.

- (17) Rebers, J. E.; Riddiford, L. M. Structure and Expression of a *Manduca Sexta* Larval Cuticle Gene Homologous to *Drosophila* Cuticle Genes. *J. Mol. Biol.* 1988, 203, 411-423, DOI 10.1016/0022-2836(88)90009-5.
- (18) Jin, C.; Zhao, J.; Pu, J.; Liu, X.; Li, J. Hichin, a Chitin Binding Protein is Essential for the Self-Assembly of Organic Frameworks and Calcium Carbonate During Shell Formation. *Int. J. Biol. Macromol.* 2019, *135*, 745-751, DOI 10.1016/j.ijbiomac.2019.05.205.
- (19) Nakayamaa, S.; Suzukia, M.; Endoa, H.; Iimuraa, K.; Kinoshitac, S.; Watabec, S.;Kogureb, T.; Nagasawaa, H. Identification and Characterization of a Matrix Protein (PPP-10) in the Periostracum of the Pearl Oyster, *Pinctada Fucata. FEBS Open Bio.* 2013, *3*, 421-427, DOI 10.1016/j.fob.2013.10.001.
- (20) Suzuki, M.; Iwashima, A.; Tsutsui, N.; Ohira, T.; Kogure, T.; Nagasawa, H. Identification and Characterisation of a Calcium Carbonate-Binding Protein, Blue Mussel Shell Protein (BMSP), from the Nacreous Layer, *Chem. Bio. Chem.* 2011, *12*, 2478-2487, DOI 10.1002/cbic.201100317.
- (21) Montagnani, C.; Marie, B.; Marin, F.; Belliard, C.; Riquet, F., Tayale, A.; Zanella-Cleon, I.; Fleury, E.; Gueguen, Y.; Piquemal, D.; Cochennec-Laureau, N. *Pmarg*-Pearlin is a Matrix Protein Involved in Nacre Framework Formation in the Pearl Oyster *Pinctada margaritifera*. *Chem. Bio. Chem.* 2011,12, 2033-2043, DOI 10.1002/cbic.201100216.
- (22) Launey, M. E.; Ritchie, R. O. On the Fracture Toughness of Advanced Materials. *Adv. Mater.* 2009, *21*, 2103-2110, DOI 10.1002/adma.200803322.
- (23) Whiffin, V. S.; Van Paassen, L. A.; Harkes, M. P. Microbial Carbonate Precipitation as a Soil Improvement Technique. *Geomicrobiol. J.* 2007, 24, 417-423, DOI 10.1080/01490450701436505.

- (24) DeJong, J. T.; Fritzges, M. B.; Nusslein, K. Microbially Induced Cementation to Control Sand Response to Undrained Shear. J. Geotech. Geoenviron. Eng. 2006, 132, 1381-1392, DOI 10.1061/(ASCE)1090-0241(2006)132:11(1381).
- (25) Gowthaman, S.; Mitsuyama, S.; Nakashima, K.; Komatsu, M.; Kawasaki, S. Biogeotechnical Approach for Slope Soil Stabilization Using Locally Isolated Bacteria and Inexpensive Low-Grade Chemicals: A Feasibility Study on Hokkaido Expressway Soil, Japan. *Soils Found.* 2019, *59*, 484-499, DOI 10.1016/j.sandf.2018.12.010.
- (26) Maroney, M. J.; Ciurli, S. Nonredox Nickel Enzymes, *Chem. Rev.* 2014, *114*, 4206-4228, DOI 10.1021/cr4004488.
- (27) Hamdan, N.; Zhao, Z.; Mujica, M.; Kavazanjian, E.; He, X. Hydrogel-Assisted Enzyme-Induced Carbonate Mineral Precipitation. J. Mater. Civ. Eng. 2016, 28, 04016089-04016098, DOI 10.1061/(A SCE)MT.1943-5533.0001604.
- (28) Zhao, Z.; Hamdan, N.; Shen, L.; Nan, H.; Almajed, A.; Kavazanjian, E.; He, X. Biomimetic Hydrogel Composites for Soil Stabilization and Contaminant Mitigation. *Environ. Sci. Technol.* 2016, *50*, 12401-12410, DOI 10.1021/acs.est.6b01285.
- (29) Yang, T.L. Chitin-Based Materials in Tissue Engineering: Applications in Soft Tissue and Epithelial Organ. *Int. J. Mol. Sci.* 2011, *12*, 1936-1963, DOI 10.3390/ijms12031936.
- (30) Hashimoto, M.; Ikegami, T.; Seino, S.; Ohuchi, N.; Fukada, H.; Sugiyama, J.; Shirakawa, M.; Watanabe, T. Expression and Characterization of the Chitin-Binding Domain of Chitinase A1 from *Bacillus circulans* WL-12. *J. Bacteriol.* 2000, *182*, 3045-3054, DOI 10.1128/JB.182.11.3045-3054.2000.
- (31) Jee, J-G; Ikegami, T.; Okada, T.; Hashimoto, M.; Seino, S.; Watanabe, T.; Shirakawa,M. Solution Structure of the Fibronectin Type III Domain From *Bacillus Circulans*

WL-12 Chitinase A1. J. Biol. Chem. 2000, 277, 1388-1397, DOI 10.1074/jbc.M109726200.

- (32) Ping, H.; Wan, Y.; Xie, H.; Xie, J.; Wang, W.; Wang, H.; Munir, Z. A.; Fu, Z. Organized Arrangement of Calcium Carbonate Crystals, Directed by a Rationally Designed Protein. *Cryst. Growth Des.* 2018, 18, 3576-3583, DOI 10.1021/acs.cgd.8b00365.
- (33) Gaskin, D. J. H.; Starck, K.; Vulfson, E. N. Identification of Inorganic Crystal-Specific Sequences Using Phage Display Combinatorial Library of Short Peptides: A Feasibility Study. *Biotechnol. Lett.* 2000, 22, 1211-1216, DOI 10.1023/A:1005603117023.
- (34) Sarikaya, M.; Tamerler, C.; Jen, A. K.; Schulten, K.; Baneyx, F. Molecular Biomimetics: Nanotechnology Through Biology. *Nat. Mater.* 2003, *2*, 577-585, DOI 10.1038/nmat964.
- (35) Danjo, T.; Kawasaki, S. Microbially Induced Sand Cementation Method Using *Pararhodobacter* sp. Strain SO1, Inspired by Beach Rock Formation Mechanism. *Mater. Trans.* 2016, 57, 428-437, DOI 10.2320/matertrans.M-M2015842.
- (36) Danjo, T.; Kawasaki, S. A study of the Formation Mechanism of Beach Rock in Okinawa, Japan: Toward Making Artificial Rock. *Int. J. GEOMATE*. 2013, *5*, 634-639, DOI 10.21660/2013.9.3157.
- (37) Nawarathna, T. H. K.; Nakashima, K.; Fujita, M.; Takatsu, M.; Kawasaki, S. Effects of Cationic Polypeptide on CaCO₃ Crystallization and Sand Solidification by Microbial-Induced Carbonate Precipitation. ACS Sustainable Chem. Eng. 2018, 6, 10315-10322, DOI 10.1021/acssuschemeng.8b01658.
- (38) Lobo, M. D.; Silva, F. D.; Landim, P. G.; da Cruz, P. R.; de Brito, T. L.; de Medeiros,S. C.; Oliveira, J. T.; Vasconcelos, I. M.; Pereira, H. D.; Grangeiro, T. B. Expression

and Efficient Secretion of a Functional Chitinase from *Chromobacterium violaceum* in *Escherichia coli*. *BMC Biotechnol*. **2013**, 13:46, DOI 10.1186/1472-6750-13-46.

- (39) Cui, J.; Yu, Z.; Lau, D. Effect of Acetyl Group on Mechanical Properties of Chitin/Chitosan Nanocrystal: A Molecular Dynamics Study. *Int. J. Mol. Sci.* 2016, *17*, 61-74, DOI 10.3390/ijms17010061.
- (40) Briegel, C.; Seto, J. Single Amino Acids as Additives Modulating CaCO: *In Advanced Topics in Biomineralization*. 2012, 33-48, DOI 10.5772/39297.
- (41) Njegic Dzakula, B.; Falini, G.; Kralj, D.; Crystal Growth Mechanism of Vaterite in the Systems Containing Charged Synthetic Poly(Amino Acids). *Croat. Chem. Acta.* 2018, *90*, 689-698, DOI 10.5562/cca3290.
- (42) Jain, G.; Pendola, M.; Huang, Y. C.; Gebauer, D.; Evans, J. S. A Model Sea Urchin Spicule Matrix Protein, rSpSM50, is a Hydrogelator that Modifies and Organizes the Mineralization Process. *Biochemistry* 2017, 56, 2663-2675, DOI 10.1021/acs.biochem.7b00083.
- (43) Nawarathna, T. H. K.; Nakashima, K.; Kawasaki, S. Chitosan Enhances Calcium Carbonate Precipitation and Solidification Mediated by Bacteria. *Int. J. Biol. Macromol.* 2019, 133, 867-874, DOI 10.1016/j.ijbiomac.2019.04.172.
- (44) Voet, D. J.; Voet, J. G.; Pratt, C. W. Fundamentals of Biochemistry, 4th ed.; John Wiley & Sons: 111 River Street, Hoboken, NJ, 2013.
- (45) Chen, T.; Small, D. A.;Wu, L. Q.; Rubloff, G. W.; Ghodssi, R.; Vazquez-Duhalt, R.; Bentley, W. E.; Payne, G. F. Nature-Inspired Creation of Protein-Polysaccharide Conjugate and Its Subsequent Assembly onto a Patterned Surface. *Langmuir* 2003, *19*, 9382-9386, DOI 10.1021/la0347096.
- (46) Treccani, L.; Mann, K.; Heinemann, F.; Fritz, M. Perlwapin, an Abalone Nacre Protein with Three Four-Disulfide Core (Whey Acidic Protein) Domains, Inhibits the

Growth of Calcium Carbonate Crystals. *Biophys. J.* **2006**, *91*, 2601-2608, DOI 10.1529/biophysj.106.086108.

- (47) Raabe, D.; Sachs, C.; Romano, P. The Crustacean Exoskeleton as an Example of a Structurally and Mechanically Graded Biological Nanocomposite Material. *Acta Mater.* 2005, 53, 4281-4292, DOI 10.1016/j.actamat.2005.05.027.
- (48) Wu, J.; Zeng, R. J. Biomimetic Regulation of Microbially Induced Calcium Carbonate Precipitation Involving Immobilization of *Sporasarcina Pasteurii* by Sodium Alginate. Cryst. Growth Des. 2017, *17*, 1854-1862, DOI 10.1021/acs.cgd.6b01813.
- (49) Trushina, D.B.; Bukreeva, T. V.; Kovalchuk, M. V.; Antipina, M. N. CaCO₃ Vaterite Microparticles for Biomedical and Personal Care Applications. Mater. Sci. Eng. C. 2014, 45, 644-658, DOI 10.1016/j.msec.2014.04.050.
- (50) Didymus, J. M.; Oliver, P.; Mann, S.; DeVries, A. L.; Hauschka, P. V.; Westbroek, P. Influence of Low-Molecular-Weight and Macromolecular Organic Additives on the Morphology of Calcium Carbonate. *J. Chem. Soc., Faraday Trans.* **1993**, *89*, 2891-2900, DOI 10.1039/FT9938902891.
- (51) Zhang, C.; Li. F.; Lv, J. Morphology and Formation Mechanism in Precipitation of Calcite Induced by *Curvibacter lanceolatus* strain HJ-1. *J. Cryst. Growth* 2017, 478, 96-101, DOI 10.1016/j.jcrysgro.2017.08.019.
- (52) Vikulina, A. S.; Feoktistova, N. A.; Balabushevich, N. G.; Skirtachd, A. G.; Volodkinab, D. The Mechanism of Catalase Loading into Porous Vaterite CaCO₃ Crystals by Co-synthesis. *Phys.Chem.Chem.Phys.* 2018, 20, 8822-8831, DOI 10.1039/c7cp07836f.
- (53) Donners, J. J. J. M.; Nolte, R. J. M.; Sommerdijk, N. A. J. M. A Shape-Persistent Polymeric Crystallization Template for CaCO₃. *J. Am. Chem. Soc.* 2002, *124*, 9700-9701, DOI 10.1021/ja0267573.

- (54) Hosoda, N.; Kato, T. Thin-Film Formation of Calcium Carbonate Crystals: Effects of Functional Groups of Matrix Polymers. *Chem. Mater.* 2001, *13*, 688-693, DOI 10.1021/cm000817r.
- (55) Dzakula, B. N.; Falini, G.; Brecevic, L.; Skoko, Z.; Kralj, D. Effects of Initial Supersaturation on Spontaneous Precipitation of Calcium Carbonate in the Presence of Charged Poly-L-Amino Acids. *J. Colloid Interface Sci.* 2009, 343, 553-563, DOI 10.1016/j.jcis.2009.12.010.
- (56) Falini, G.; Fermani, S.; Gazzano, M.; Ripamonti, A. Oriented Crystallization of Vaterite in Collagenous Matrices. *Chem.Eur. J.* 1998, *4*, 1048 – 1052, DOI 10.1002/(SICI)1521-3765(19980615)4:6<1048::AID-CHEM1048>3.0.CO;2-U.
- (57) Parakhonski, B. V.; Yashchenok, A. M.; Donatan, S.; Volodkin, D. V.; Tessarolo, F.;
 Antolini, R.; Mçhwald, H.; Skirtach, A. G. Macromolecule Loading into Spherical,
 Elliptical, Star-Like and Cubic Calcium Carbonate Carriers. *Chem. Phys. Chem.* 2014, 15, 1-7, DOI 10.1002/cphc.201402136.
- (58) Oral, C. M.; Ercan, B. Influence of pH on Morphology, Size and Polymorph of Room Temperature Synthesized Calcium Carbonate Particles. *Powder Technol.* 2018, *339*, 781-788, DOI 10.1016/j.powtec.2018.08.066.
- (59) Majorek, K. A.; Porebski, P. J.; Dayal, A.; Zimmerman, M. D.; Jablonska, K.; Stewart,
 A. J.; Chruszcz, M.; Minor, W. Structural and Immunologic Characterization of
 Bovine, Horse, and Rabbit Serum Albumins. *Mol. Immunol.* 2012, *52*, 174-182, DOI
 10.1016/j.molimm.2012.05.011.
- (60) Bate, B.; Cao, J.; Zhang, C.; Hao, N. Spectral Induced Polarization Study on Enzyme Induced Carbonate Precipitations: Influences of Size and Content on Stiffness of a Fine Sand. Acta Geotech. 2021, 16, 841-857, DOI 10.1007/s11440-020-01059-8.
- (61) Liu, K. W.; Jiang, N. J.; Qin, J. D.; Wang, Y. J.; Tang, C. S.; Han, X. L. An

Experimental Study of Mitigating Coastal Sand Dune Erosion by Microbial- and Enzymatic-Induced Carbonate Precipitation. *Acta Geotech.* **2021**, *16*, 467-480, DOI 10.1007/s11440-020-01046-z.

- (62) Harkes, M. P.; Paassen, L. A. V.; Booster, J. L.; Whiffin, V. S.; Loosdrechta, M. C. M. V. Fixation and Distribution of Bacterial Activity in Sand to Induce Carbonate Precipitation for Ground Reinforcement. *Ecol. Eng.* 2010, *36*, 112-117, DOI 10.1016/j.ecoleng.2009.01.004.
- (63) Fujita, M.; Nakashima, K.; Achal, V.; Kawasaki S. Whole-cell Evaluation of Urease Activity of *Pararhodobacter sp.* Isolated from Peripheral Beach Rock. *Biochem. Eng. J.* 2017, *124*, 1-5, DOI 10.1016/j.bej.2017.04.004.
- (64) Rahman, Md. M.; Hora, R. N.; Ahenkorah, I.; Beecham, S.; Karim, Md, R.; Iqbal, A. State-of-the-Art Review of Microbial-Induced Calcite Precipitation and Its Sustainability in Engineering Applications. *Sustainability* 2020, 12, 6281-6322, DOI 10.3390/su12156281.



Fig. 1 Structure and function of CaBP-ChBD: (A) Schematic ribbon drawing and the amino acid sequence of CaBP-ChBD and (B) CaCO₃ formation on chitin through the fusion protein.



Fig. 2 Binding assay of CaBP-ChBD on chitin particles evaluated by (A) the protein concentration in the supernatant by Bradford assay and (B) SDS-PAGE.



Fig. 3 Amount of CaCO₃ precipitate in the presence of proteins with or without chitin.



Fig. 4 SEM images of the CaCO₃ precipitate: (a) None (control), (b) with CaBP-ChBD, (c) with Chitin, and (d) with CaBP-ChBD and chitin. Images with a blue frame indicate the magnified views of (b) and (d).



Fig. 5 EDS analysis of the CaCO₃ precipitate: (a) None (control), (b) with CaBP-ChBD, (c) with Chitin, and (d) with CaBP-ChBD and chitin.



Fig. 6 XRD patterns of the CaCO₃ precipitate: (a) None (control), (b) with CaBP-ChBD, (c) with Chitin, and (d) with CaBP-ChBD and chitin.



Fig. 7 SEM images of solidified samples by EICP: (a) None (control), (b) with CaBP-ChBD, (c) with Chitin, (d) with CaBP-ChBD and chitin.

For Table of Contents Use Only



Synopsis

Developed recombinant protein can effectively form CaCO₃ on chitin and increase the efficiency of the bio-cementation more sustainably.